

Chopped Strand Mat M2 (powder bound)

Product sheet

Product description

E Glass, powder bound, chopped strand mat for general reinforcement. Filament diameter 12µm.

Uses

Reinforcement of cracks and daywork joints or other low movement situations in conjunction with Flowchem VE resins.

Density

The product is available in two densities.

300 g/m² +/-10%. 450 g/m² +/-10%.

Storage

Chopped strand mat should be stored in the original packaging and protected from impact damage. It is recommended that glass fibre be kept at a temperature not exceeding 25°C and a relative humidity of 65% ± 10%.

Boxes of chopped strand mat should preferably be stored on end. If boxes are stored on their sides, no more than three boxes should be stacked on top of each other if damage to the mat is to be avoided.

A First-In-First-Out (FIFO) stock control system is recommended to minimize the influence of storage conditions.

Packaging

Roll width (+/-1%)	Roll weight (+/-10%)	Roll diameter
0.95 m	30 kg	approx. 28 cm

Each roll supplied in a polythene bag and cardboard box.

Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.