



# superflex wide joint

## Tile Grout for joints 3mm-20mm

### DESCRIPTION

Water/frost-resistant highly flexible cementitious tile grout for walls and floors.

#### Use for

- Grouting porcelain, glazed and fully vitrified tiles, glass and ceramic mosaics, marble and natural stone in dry or wet interior and exterior environments.
- For joint widths: up to **3mm to 20mm**
- Recommended for swimming pools, and for limited movement areas including overlaid plywood floors (minimum 15mm) and heated screeds.

#### Restrictions: NOT suitable for

- Food preparation/storage areas, and areas requiring waterproof grouting.

NOTE: Use a BAL Epoxy grout in these cases.

#### PRODUCT INFORMATION

**Composition:** Cement-based powder with built-in admixture.

**Colours:** White, Ivory, Grey, Charcoal, Limestone, Sandstone

**Type/Classification:** Exceeds BS EN 13888 **CG2**

**Pack sizes:** 10kg and 3.5kg

**Key features:** Water/frost-resistant. Built-in admixture for increased flexibility and high bond strength at edges of tiles/mosaics.

### USAGE & SERVICE CONDITIONS

Walls	✓	Floors	✓
Interior	✓	Exterior	✓
Dry	✓	Showers (1)	✓

Swimming Pools (2)	✓
Movement/Vibration	✓
Heavily Trafficked Floors	✓

- (1) Use a BAL epoxy grout for power shower with body jets. Do not use shower for at least 2 weeks following completion of grouting – BS 5385:Part 4:2009, clause 7.2.1.
- (2) Do not fill pool for at least 3 weeks following completion of grouting – BS 5385:Part 4:2009, clause 7.2.10.

Mix/Usage Data			
Powder:Water Ratio (by weight)	Pot Life at 20°C	Cure Time at 20°C*	Specific Gravity
5:1	30 mins	24 hours	1.70g/cm <sup>3</sup>

\* Drying time will be extended in colder temperatures, when fixing to impervious backgrounds or when fixing tiles of low porosity.

Coverage		
Tile Size	Joint Width	Typical Coverage
200x200x9mm	3mm	2.24m <sup>2</sup> /kg
300x300x9mm	3mm	3.33m <sup>2</sup> /kg

Temperature Resistance
-30°C to 150°C

## SURFACE PREPARATION

### General

Before grouting, ensure that:

1. Tile adhesive has fully set, as indicated on adhesive packaging.
2. Open joints are protected from contamination – and are clean, dry and free from loose debris.

**IMPORTANT NOTE:** Do NOT use in temperatures below 5°C or in damp conditions.

*If grouting porous tiles in temperatures above 25°C, dampen joints with clean water prior to grouting.*

*If grouting externally, provide protection against inclement weather during grouting and for as long as possible afterwards.*

*If grouting shower installations, BAL SUPERFLEX WIDE JOINT is water-resistant but NOT impervious to water and is not a substitute for tanking systems.*

*Recommendations (showers):*

- Provide waterproof tanking protection for tiling background substrates, particularly plaster or plasterboard (e.g. by using BAL WATERPROOFING KIT FOR SHOWERS).
- Ensure tiles are fixed with a water-resistant adhesive (e.g. BAL WHITE STAR, BAL MOSAIC-FIX or BAL SINGLE PART FLEXIBLE adhesive).

### MIXING

1. Slowly add 5 parts powder to 1 part clean cold water by weight (e.g. 1kg powder with 0.2 litres water). Mix until smooth paste formed.

*NOTE: If using electric drill mixer, blend at slow speed (i.e. under 300rpm).*

2. Wait 2-3 minutes, then briefly mix again. Avoid entraining air by mixing at too high speed or by over-mixing.

Mixed grout working time at 20°C: approx. 30 minutes.

**NOTE:**

Do NOT add more water to mixed grout as this would reduce final strength.

Working time/setting time will vary slightly with temperature:  
higher temperatures = shorter; lower temperatures = longer.

## APPLICATION

### Grouting procedure

1. Check potential staining risk: apply grout to a few tiles in small trial area. If discolouration occurs or difficulties are encountered with cleaning off (surplus grout), apply BAL PROTECTIVE SEALER – and repeat trial.
2. Work in small areas with a BAL GROUT FLOAT or squeegee. Completely fill tile joints with mixed grout and compact well, removing excess grout from tile surface as work proceeds.
3. Allow approx. 15 minutes for grout to dry before cleaning tile surface.
4. Using a dampened sponge or sponge board, clean surface diagonally to grout lines. Rinse out sponge/sponge board frequently with clean water.
5. When grout has set sufficiently within joints, polish tile surface with dry clean cloth OR give surface final wash with dampened sponge and clean cold water.

**NOTE:** For maximum speed/ease, use a BAL Wash Boy.

6. Wait minimum 24 hours before subjecting tiles to normal service conditions.

**NOTE:**

When grouting soft glazed wall tiles or tiles with a metal decor or lustre, care should be taken to ensure they are not damaged/scratched. If there is any doubt, a test area should first be grouted in an inconspicuous area.

*If completing a swimming pool, do NOT fill pool for at least 3 weeks after grouting (contact BAL Technical Advisory Service for further advice).*

*If completing a shower, do NOT use shower for at least 2 weeks (as required by BS 5385: Part 4:2009, clause 7.2.1).*

### CLEANING

Always use cleaning products suited to tile type. For best long-term antibacterial protection, regular cleaning with BAL MICROSHIELD TILE CLEANER is strongly recommended.

## **HEALTH & SAFETY INFORMATION/ GOOD PRACTICE ADVICE**

For detailed information and safety guidance, please refer to Product Material Safety Data Sheet [MSDS].

## **TECHNICAL ADVISORY SERVICE**

For free expert guidance on use of this product, or any aspect of tiling, contact the BAL TECHNICAL ADVISORY AND SPECIFICATION SERVICE on  
Tel: 01782 591120 or 0845 600 1 222 or Fax: 01782 591121.

## **POWERSPEC**

A unique computerised online specification system for the design and installation of ceramic, mosaic and natural stone tiling. Visit [www.powerspeconline.com](http://www.powerspeconline.com)

## **SHELF LIFE**

12 months under normal dry conditions. Protect from frost and damp.

## **QUALITY AND ENVIRONMENTAL STANDARDS**

Manufacturing quality assurance standards conform to BS EN ISO 9001. Satisfies the environmental management requirements and operational scope of ISO 14001.

## **25 YEAR GUARANTEE**

All BAL products are supplied with a 25 year product guarantee to be free from manufacturing defects and to be fit for purpose. The guarantee covers materials replacement costs and labour.

This guarantee is subject to use of product in accordance with BAL's instructions and technical data, and good working practice. No liability can be accepted for any loss or damage arising from incorrect use of products or poor workmanship, over which BAL has no control.

*Contact BAL Marketing Department for full details.*

## **CONDITIONS OF SALE**

Sold subject to the Company's Conditions of Sale.  
*Available on request.*

*For sales and technical queries, contact:*

### **BUILDING ADHESIVES LTD**

Longton Road, Trentham, Stoke-on-Trent, ST4 8JB, England  
[www.bal-adhesives.com](http://www.bal-adhesives.com)

Sales

Tel: +44 (0) 1782 591160

Fax: +44 (0) 1782 591131

Technical

Tel: +44 (0) 1782 591120 or  
+44 (0) 845 600 1 222

Fax: +44 (0) 1782 591121

Unit 622, Phase III  
Northwest Business Park  
Ballycoolin, Dublin 15, Ireland

Tel: +353 (0) 1 880 9210

Fax: +353 (0) 1 880 9211

NOTE: BAL reserves the right to update instructions, technical data and other information at any time without notice.

PorcelBond Plus™ is a trademark of Building Adhesives Ltd.

 **Powerspec**  
[www.powerspeconline.com](http://www.powerspeconline.com)



 **BAL**

**Superflex Wide Joint**